GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A231

Standard Specification for Chromium-Vanadium Alloy Steel Spring Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A231 Chromium-Vanadium Alloy Steel Spring Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Wire

Chemical Composition		
Carbon	C %	0.480 - 0.530
Manganese	Mn %	0.700 - 0.900
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Silicon	Si %	0.150 - 0.350
Chromium	Cr %	0.800 - 1.100
Vanadium	V %	0.150 min.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing

Mechanical Properties	
Tensile Strength in Mpa	1320 - 1460
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	40 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K15048	UNS	USA	Steel
K15047	UNS	USA	Steel
A 232	ASTM	USA	Wire
S 204	B.S.	United Kingdom	Wire
970-5 735 A 50	B.S.	United Kingdom	Steel
J 132	SAE	USA	Wire
SA-232	ASME	USA	Wire

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.