

Material - ASTM A240 UNS N08020

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|------------------|-------------------------------|----------|
| Carbon | C % | 0.070 max. | | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Phosphorus | P % | 0.045 max. | Solution Annealing | |
| Sulphur | S % | 0.035 max. | | |
| Chromium | Cr % | 19.000 - 21.000 | | |
| Nickel | Ni % | 32.000 - 38.000 | | |
| Molybdenum | Mo % | 2.000 - 3.000 | | |
| Niobium | Nb % | 8*C - 1.000 max. | Mechanical Properties | |
| Copper | Cu % | 3.000 - 4.000 | Tensile Strength in Mpa | 550 min. |
| Iron | Fe % | Balance | Yield Strength in Mpa | 240 min. |
| - | - | - | Elongation in % | 30 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardn <mark>ess in HB</mark> | 217 max. |
| - | - | | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| A 182 F 20 | ASTM | USA | Forging | |
| A358 N08020 | ASTM | USA | Steel and Pipe | |
| A 959 N08020 | ASTM | USA | Steel | |
| N08020 | UNS | USA | Steel | |
| N08321 | UNS | USA | Steel | |
| NiCr20CuMo | DIN | Germany | Steel | |
| B463 N08020 | ASTM | USA | Steel | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.