

Material - ASTM A240 UNS N08367

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------------|----------|
| Carbon | C % | 0.030 max. | Solution Annealing | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 1.500 max. | | |
| Phosphorus | P % | 0.040 max. | | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 20.000 - 22.000 | | |
| Nickel | Ni % | 23.500 - 25.500 | | |
| Molybdenum | Mo % | 6.000 - 7.000 | | - |
| Nitrogen | N % | 0.180 - 0.250 | Mechanical Properties | |
| Copper | Cu % | 0.750 max. | Tensile Strength in Mpa | 690 min. |
| Iron | Fe % | Balance | Yield Strength in Mpa | 310 min. |
| - | - | - | Elongation in % | 30 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | | |
|--------------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| SA-351 CN3MN | ASME | USA | Casting | | |
| 1.4585 | DIN | Germany | Casting | | |
| J94651 | UNS | USA | Casting | | |
| Ao X 10 CrNiMoCuNb 18-18 | MSZ | Hungary | Casting | | |
| G X 7 CrNiMoCuNb 18-18 | DIN | Germany | Casting | | |
| A743 CN3MN | ASTM | USA | Casting | | |
| A744 CN3MN | ASTM | USA | Casting | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.