

## Material - ASTM A240 UNS S30103

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Nickel	Ni %	6.000 - 8.000		
Nitrogen	N %	0.200 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	220 min.
-	-	-	Elongation in %	45 min.
-	-	-	Reduction of Area in %	•
-	-	-	Hardness in HB	241 max.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
301	AISI	USA	Steel, Sheet, Bar and Strip	
301	SAE	USA	Steel	
301 S 21	BS	British	Steel, Plate, Sheet and Strip	
STS 301	KS	Korea	Steel, Plate, Sheet and Strip	
S30100	UNS	USA	Steel	
301	AS	Australia	Steel, Plate, Sheet and Strip	
S30103	UNS	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.