

Material - ASTM A240 UNS S32750

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.200 max.	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	3.000 - 5.000		
Nitrogen	N %	0.240 - 0.320	Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	795 min.
Iron	Fe %	Balance	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	310 max.
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
S32750	UNS	USA	Steel	
G X2CrNiMoN26-7-4	AFNOR NF	France	Casting	
1.4469	EN	European Union	Casting	
GX2CrNiMoN26-7-4	DIN	Germany	Casting	
GX2CrNiMoN25-7-4	DIN	Germany	Casting	
J93404	UNS	USA	Casting	
1.4469	DIN	Germany	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.