



## Material - ASTM A240 UNS S33228

**Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel, Plate, Sheet and Strip**

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080	Solution Annealing	
Silicon	Si %	0.300 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	26.000 - 28.000		
Nickel	Ni %	31.000 - 33.000		
Cerium	Ce %	0.050 - 0.100		
Niobium	Nb %	0.600 - 1.000		
Aluminium	Al %	0.025 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      500 min. Yield Strength in Mpa      185 min. Elongation in %      30 min. Reduction of Area in %      - Hardness in BHN      217 max. Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S33228	UNS	USA	Steel
A167 S33228	ASTM	USA	Steel, Sheet, Plate and Strip
A213 S33228	ASTM	USA	Steel and Tube
A312 S33228	ASTM	USA	Steel and Pipe
A249 S33228	ASTM	USA	Steel and Tube
A479 S33228	ASTM	USA	Steel and Bar
A959 S33228	ASTM	USA	Steel

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.