GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A254

Standard Specification for Copper-Brazed Steel Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A254 Copper-Brazed Steel Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tubing

Chemical Composition		
Carbon	C %	0.050 - 0.150
Manganese	Mn %	0.270 - 0.630
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	290 min.
Yield Strength in Mpa	172 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K01001	UNS	USA	Steel
A 178 Grade A	ASTM	USA	Tubing
A 192	ASTM	USA	Tubing
G 3461 STB 35	JIS	Japan	Tubing
17175 1.0305	DIN	Germany	Steel
17175 St 35.8	DIN	Germany	Steel
SA-179	ASME	USA	Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.