GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A268 TP429

Standard Specification for Seamless and Welded Ferritic and Martensitic Stainless Steel Tubing for General Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A268 TP429 Seamless and Welded Ferritic and Martensitic Stainless Steel Tubing for General Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Tubing

Chemical Composition		
Carbon	C %	0.120 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	14.000 - 16.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Annealing or Tempering

Mechanical Properties	
Tensile Strength in Mpa	415 min.
Yield Strength in Mpa	240 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	190 max.
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S42900	UNS	USA	Steel
G 4304 SUS 429	JIS	Japan	Plate, Sheet and Strip
D 3698 STS 429	KS	Korea	Plate, Sheet and Strip
J 405 429	SAE	USA	Steel
A 276 429	ASTM	USA	Bars and Shapes
A 240 Type 429	ASTM	USA	Plate, Sheet and Strip
A 959 Type 429	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.