GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A276 UNS S31654

Standard Specification for Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A276 UNS S31654 Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.030 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	16.000 - 18.000
Nickel	Ni %	10.000 - 13.000
Molybdenum	Mo %	2.000 - 3.000
Nitrogen	N %	0.160 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	345 min.
Elongation in %	30 min.
Reduction of Area in %	50 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
D 3698 STS 316LN	KS	Korea	Plate, Sheet and Strip
G 4305 SUS 316 LN	JIS	Japan	Plate, Sheet and Strip
SA-276 S31654	ASME	USA	Bars and Shapes
A 959 Type 316LN	ASTM	USA	Steel
A 194 Grade 8MLN	ASTM	USA	Steel
A 358 316LN	ASTM	USA	Steel and Pipe
A 959 Type 316LHN	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.