GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A289 Grade 6

Standard Specification for Alloy Steel Forgings for Nonmagnetic Retaining Rings for Generators

Group - Ferrous Stainless Steel Alloys
Sub Group - ASTM A289 Grade 6 Alloy Steel Forgings for Nonmagnetic Retaining Rings for Generators
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.100 max.
Manganese	Mn %	17.500 - 20.000
Phosphorus	P %	0.060 max.
Sulphur	S %	0.015 max.
Silicon	Si %	0.800 max.
Nickel	Ni %	2.000 max.
Chromium	Cr %	17.500 - 20.000
Nitrogen	N %	0.450 - 0.800
Titanium	Ti %	0.100 max.
Aluminium	Al %	0.040 max.
Vanadium	V %	0.250 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	1275 min.
Yield Strength in Mpa	1240 min.
Elongation in %	14 min.
Reduction of Area in %	40 min.
Hardness in HB	-
Impact in Joule	68 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S28200	UNS	USA	Steel
A 276 S28200	ASTM	USA	Bars and Shapes
A 493 S28200	ASTM	USA	Wire and Wire Rods
A 580 S28200	ASTM	USA	Steel and Wire
A 959 S28200	ASTM	USA	Steel
SEW 390 1.3816	DIN	Germany	Steel
SEW 390 X8CrMnN18-18	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.