GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A29 M1010

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for

Group - Ferrous Mild Steel Alloys
Sub Group - ASTM A29 M1010 Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel and Bars

Chemical Composition		
Carbon	C %	0.070 - 0.140
Manganese	Mn %	0.250 - 0.600
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Normalizing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G10100	UNS	USA	Steel, Forging and Bars
SA-29 M1010	ASME	USA	Steel and Bars
J 467 M1010	SAE	USA	Steel
M1010	AISI	USA	Steel
A 575 M1010	ASTM	USA	Steel and Bars
A 519 1010	ASTM	USA	Steel and Tubing
A 108 1010	ASTM	USA	Steel and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.