



**GRAVITY CAST PVT. LTD.**  
GRAVITY GROUP OF COMPANIES

## Material - ASTM A297 Grade HF

Standard Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A297/ A297M Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.400	As - Cast	
Silicon	Si %	2.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	18.000 - 23.000		
Nickel	Ni %	8.000 - 12.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      485 min. Yield Strength in Mpa      240 min. Elongation in %      25 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J92603	UNS	USA	Casting
1.4826	DIN	Germany	Casting
SCH 12	JIS	Japan	Casting
G X 30 CrNi 20-10	UNI	Italy	Casting
AM-X 30 CrNi 20-10	UNE	Spain	Casting
422934	CSN	Czech Republic	Casting
G X 40 CrNiSi 22-9	DIN	Germany	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**