GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A333 Grade 3

Standard Specification for Seamless and Welded Steel Pipe for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A333 Grade 3 Seamless and Welded Steel Pipe for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition		
Carbon	C %	0.190 max.
Manganese	Mn %	0.310 - 0.640
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Silicon	Si %	0.180 - 0.370
Nickel	Ni %	3.180 - 3.820
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Normalizing

Mechanical Properties	
Tensile Strength in Mpa	450 min.
Yield Strength in Mpa	240 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	18 @ -100˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K31918	UNS	USA	Steel
SAE J 1249 A 2317	AISI	USA	Steel
A 334 Grade 3	ASTM	USA	Tubing
A 420 Grade WPL 3	ASTM	USA	Pipe
16 Ni 14	DIN	Germany	Steel
G 3205 SFL 3	JIS	Japan	Forging
J 1249 2317	SAE	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.