GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A333 Grade 8

Standard Specification for Seamless and Welded Steel Pipe for Low-Temperature Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A333 Grade 8 Seamless and Welded Steel Pipe for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition		
Carbon	C %	0.130 max.
Manganese	Mn %	0.900 max.
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Silicon	Si %	0.130 - 0.320
Nickel	Ni %	8.400 - 9.600
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Normalizing or Double Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	515 min.
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	18 @ -195˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K81340	UNS	USA	Steel
SA-333 Grade 8	ASME	USA	Pipe
SA-334 Grade 8	ASME	USA	Tubing
SA-522 Type I	ASME	USA	Steel
A 522 Type I	ASTM	USA	Steel
A 334 Grade 8	ASTM	USA	Tubing
A 353	ASTM	USA	Steel and Plates

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.