GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A336 Grade F3VCb

Standard Specification for Alloy Steel Forgings for Pressure and High-Temperature Parts

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A336 Grade F3VCb Steel Forgings for Pressure and High-Temperature Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.100 - 0.150
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.020 max.
Sulphur	S %	0.010 max.
Silicon	Si %	0.100 max.
Nickel	Ni %	0.250 max.
Chromium	Cr %	2.700 - 3.300
Niobium	Nb %	0.015 - 0.070
Molybdenum	Mo %	0.900 - 1.100
Vanadium	V %	0.200 - 0.300
Copper	Cu %	0.250 max.
Calcium	Ca %	0.0005 - 0.0150
Titanium	Ti %	0.015 max.
Iron	Fe %	Balance
-	-	-

Heat Treatment
As-Raw or Normalizing or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	585 - 760
Yield Strength in Mpa	415 min.
Elongation in %	18 min.
Reduction of Area in %	45 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K31390	UNS	USA	Steel
SA-542 Type E Class 4a	ASME	USA	Steel and Plate
A 182 F3VCb	ASTM	USA	Steel and Pipe
A 542 Type E Class 4	ASTM	USA	Steel and Plate
A 541 Grade 3VCb	ASTM	USA	Steel and Forging
A 542 Type E Class 4a	ASTM	USA	Steel and Plate
A 508 Grade 3VCb	ASTM	USA	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.