GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A351 CF3A

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A351 CF3A Castings, Austenitic, for Pressure-Containing Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	0.030 max.
Manganese	Mn %	1.500 max.
Silicon	Si %	2.000 max.
Sulphur	S %	0.040 max.
Phosphorus	P %	0.040 max.
Chromium	Cr %	17.000 - 21.000
Nickel	Ni %	8.000 - 12.000
Molybdenum	Mo %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	530 min.
Yield Strength in Mpa	240 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J92700	UNS	USA	Steel
3100 304 C 12	B.S.	United Kingdom	Steel
SA-351 Grade CF3A	ASME	USA	Casting
SA-351 Grade CF3	ASME	USA	Casting
A 743 Grade CF-3	ASTM	USA	Casting
A 744 Grade CF-3	ASTM	USA	Casting
A 451 Grade CPF3	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.