



Material - ASTM A351 CG8M

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A351 / 351M Castings, Austenitic, for Pressure-Containing Parts
Application - Intended for Valves, Pumps, General Engineering, Automobile and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	18.000 - 21.000		
Nickel	Ni %	9.000 - 13.000		
Molybdenum	Mo %	3.000 - 4.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A743 CG8M	ASTM	USA	Casting	
A744 CG8M	ASTM	USA	Casting	
SA-351 Grade CG8M	ASME	USA	Casting	
317 C 16	BS	British	Casting	
1.4448	DIN	Germany	Casting	
389 G X 8 CrNiMo 19-11-4	SFS	Finland	Casting	
J93000	UNS	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.