



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - ASTM A352 CA6NM

**Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - ASTM A352 / A352M Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Casting**

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b>	
-	-	-	Tensile Strength in Mpa	760 - 930
-	-	-	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 min. @ -73°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ASTM A743 CA6NM	ASTM	USA	Casting
A356 CA6NM	ASTM	USA	Casting
A487 CA6NM	ASTM	USA	Casting
SA-352 Grade CA6NM	ASME	USA	Casting
SA-487 Grade CA6NMA	ASME	USA	Casting
SA-487 Grade CA6NMB	ASME	USA	Casting
SA-487 Class CA6NM	ASME	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**