



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A352 LCC

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A352 / A352M Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 - 655
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	20 min. @ -46°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J02505	UNS	USA	Casting
SA 352 LCC	ASME	USA	Casting
SA 660 WCC	ASME	USA	Centrifugal Casting
J02503	UNS	USA	Casting
A216 WCB	ASTM	USA	Casting
1.0619	EN	European Union	Casting
1.0619	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS