GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A403 CRS32053

Standard Specification for Wrought Austenitic Stainless Steel Piping Fittings

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A403 CRS32053 Wrought Austenitic Stainless Steel Piping Fittings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Pipe

Chemical Composition		
Carbon	C %	0.030 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.010 max.
Silicon	Si %	1.000 max.
Nickel	Ni %	24.000 - 26.000
Chromium	Cr %	22.000 - 24.000
Molybdenum	Mo %	5.000 - 6.000
Nitrogen	N %	0.170 - 0.220
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	640 min.
Yield Strength in Mpa	295 min.
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G 3463 SUS 836 LTB	JIS	Japan	Steel and Tubing
G 3459 SUS 836 LTP	JIS	Japan	Steel and Pipe
G 4304 SUS 836L	JIS	Japan	Plate, Sheet and Strip
D 3576 STS 836LTP	KS	Korea	Steel and Pipe
D 3698 STS 836L	KS	Korea	Plate, Sheet and Strip
SA-240 S32053	ASME	USA	Plate, Sheet and Strip
A 409 S32053	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.