GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A436 Type 4

Standard Specification for Austenitic Gray Iron Castings

Group - Ferrous Gray Iron Alloys

Sub Group - ASTM A436 Type 4 Austenitic Gray Iron Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	2.600 max.
Silicon	Si %	5.000 - 6.000
Manganese	Mn %	0.500 - 1.500
Nickel	Ni %	29.000 - 32.000
Copper	Cu %	0.500 max.
Chromium	Cr %	4.500 - 5.500
Sulphur	S %	0.120 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	172 min.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	212 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
F41005	UNS	USA	Casting
G 5510 FCA-NiSiCr 30 5 5	JIS	Japan	Casting
1694 GGL-NiSiCr 30 5 5	DIN	Germany	Casting
1694 0.6680	DIN	Germany	Casting
32-301 FGL Ni30 Si5 Cr5	AFNOR NF	France	Casting
32-301 FGS Ni30 Cr5	AFNOR NF	France	Casting
A 439 Type D-4	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.