GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A439 Type D-3

Standard Specification for Austenitic Ductile Iron Castings

Group - Ferrous Ductile Iron Alloys

Sub Group - ASTM A439 Type D-3 Austenitic Ductile Iron Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	2.600 max.
Silicon	Si %	1.000 - 2.800
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.080 max.
Nickel	Ni %	28.000 - 32.000
Chromium	Cr %	2.500 - 3.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Stress Relieved

Mechanical Properties	
Tensile Strength in Mpa	379 min.
Yield Strength in Mpa	207 min.
Elongation in %	6 min.
Reduction of Area in %	-
Hardness in HB	139 - 202
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
F43003	UNS	USA	Casting
3469 S3	B.S.	United Kingdom	Casting
1694 GGG-NiCr 30 3	DIN	Germany	Casting
1694 0.7676	DIN	Germany	Casting
1694 0.6676	DIN	Germany	Casting
7737 S-Ni Cr 30 3	UNI	Italy	Casting
32-301 FGL Ni30 Cr3	AFNOR NF	France	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.