GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A473 Type 310S

Standard Specification for Stainless Steel Forgings

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A473 Type 310S Stainless Steel Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.080 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.500 max.
Chromium	Cr %	24.000 - 26.000
Nickel	Ni %	19.000 - 22.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	515 min.
Yield Strength in Mpa	205 min.
Elongation in %	40 min.
Reduction of Area in %	50 min.
Hardness in HRC	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S31008	UNS	USA	Steel
A 403 WP 310S	ASTM	USA	Steel
A 479 310S	ASTM	USA	Steel and Bars
D 3576 STS 310STP	KS	Korea	Steeland Pipe
G 4319 SUS 310 SFB	JIS	Japan	Forging
4955 X 6 CrNi 25 21	ISO	International	Steel
SA-276 310S	ASME	USA	Bars and Shapes

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.