GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A473 Type 429

Standard Specification for Stainless Steel Forgings

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A473 Type 429 Stainless Steel Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.120 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	14.000 - 16.000
Nickel	Ni %	0.750 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing

Mechanical Properties	
Tensile Strength in Mpa	450 min.
Yield Strength in Mpa	240 min.
Elongation in %	23 min.
Reduction of Area in %	45 min.
Hardness in HRC	207 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S42900	UNS	USA	Steel
D 3698 STS 429	KS	Korea	Plate, Sheet and Strip
G 4304 SUS 429	JIS	Japan	Plate, Sheet and Strip
A 176 Type 429	ASTM	USA	Plate, Sheet and Strip
A 182 F 429	ASTM	USA	Steel and Pipe
SA-182 Grade F 429	ASME	USA	Steel and Pipe
SA-240 Type 429	ASME	USA	Plate, Sheet and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.