GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A479 Type XM-30

Standard Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A479 Type XM-30 Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.180 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	11.500 - 13.500
Niobium	Nb %	0.050 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	275 min.
Elongation in %	13 min.
Reduction of Area in %	45 min.
Hardness in HB	235 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S41040	UNS	USA	Steel
SA-479 Type XM-30	ASME	USA	Bars and Shapes
SA-276 XM-30	ASME	USA	Bars and Shapes
SA-790 S41040	ASME	USA	Bars and Shapes
SA-276 S41040	ASME	USA	Bars and Shapes
A 959 Type 410Cb	ASTM	USA	Steel
A 276 Type XM-30	ASTM	USA	Steel and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.