



Material - ASTM A493 S44700

Standard Specification for Stainless Steel Wire and Wire Rods for Cold Heading and Cold Forging

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 493 Stainless Steel Wire and Wire Rods for Cold Heading and Cold Forging Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|-----------|-----------------|---|----------|
| Carbon | C % | 0.010 max. | | |
| Silicon | Si % | 0.200 max. | | |
| Manganese | Mn % | 0.300 max. | | |
| Phosphorus | P % | 0.025 max. | Normalising or Annealing or Hardening + Tempering | |
| Sulphur | S % | 0.020 max. | | |
| Chromium | Cr % | 28.000 - 30.000 | | |
| Molybdenum | Mo % | 3.500 - 4.200 | | |
| Nickel | Ni % | 0.150 max. | | |
| C + N | C % + N % | 0.025 max. | Mechanical Properties | |
| Nitrogen | N % | 0.020 max. | Tensile Strength in Mpa | 725 max. |
| Copper | Cu % | 0.150 max. | Yield Strength in Mpa | - |
| Iron | Fe % | Balance | Elongation in % | - |
| - | - | | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| S44700 | UNS | USA | Plate, Sheet and Strip | |
| A176 S44700 | ASTM | USA | Plate, Sheet and Strip | |
| A268 29-4 | ASTM | USA | Tube | |
| SA-731 29-4 | ASME | USA | Plate, Sheet and Strip | |
| A580 S44700 | ASTM | USA | Wire | |
| A791 Grade 29-4 | ASTM | USA | Tube | |
| A731 29-4 | ASTM | USA | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.