GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A508 Grade 1

Standard Specification for Quenched and Tempered Vacuum-Treated Carbon and Alloy Steel Forgings for Pressure Vessels

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A508 Grade 1 Quenched and Tempered Vacuum-Treated Carbon and Alloy Steel Forgings for Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.350 max.
Manganese	Mn %	0.400 - 1.050
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Silicon	Si %	0.400 max.
Nickel	Ni %	0.400 max.
Chromium	Cr %	0.250 max.
Molybdenum	Mo %	0.100 max.
Vanadium	V %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	485 - 655
Yield Strength in Mpa	250 min.
Elongation in %	20 min.
Reduction of Area in %	38 min.
Hardness in HB	-
Impact in Joule	20 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K13502	UNS	USA	Steel
SA-266 Class 1	ASME	USA	Steel and Forging
SA-266 Class 2	ASME	USA	Steel and Forging
SA-541 Class 1	ASME	USA	Steel and Forging
SA-508 Grade 1	ASME	USA	Steel and Forging
A 541 Grade 1	ASTM	USA	Steel and Forging
A266 Grade 1	ASTM	USA	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.