GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A510 1211

Standard Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel

Group - Ferrous Mild Steel Alloys
Sub Group - ASTM A510 1211 General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Wire Rods and Coarse Round Wire

Chemical Composition		
Carbon	C %	0.130 max.
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.070 - 0.120
Sulphur	S %	0.100 - 0.150
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRC	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G12110	UNS	USA	Steel
J 1397 1211	SAE	USA	Steel and Bars
1211	AISI	USA	Steel
A 29 1211	ASTM	USA	Steel and Bars
A 29 12L11	ASTM	USA	Steel and Bars
A 108 1211	ASTM	USA	Steel and Bars
A 576 1211	ASTM	USA	Steel and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.