

Material - ASTM A511 29-4-2

Standard Specification for Seamless Ferritic Stainless Steel Mechanical Tubing

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 511 29-4-2 Seamless Ferritic Stainless Steel Mechanical Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Tube

| Chemical Composition | | | Heat Treatment | |
|----------------------|-----------|-----------------|---|----------|
| Carbon | C % | 0.010 max. | Normalising or Annealing or Hardening + Tempering | |
| Silicon | Si % | 0.200 max. | | |
| Manganese | Mn % | 0.300 max. | | |
| Phosphorus | Р% | 0.025 max. | | |
| Sulphur | S % | 0.020 max. | | |
| Chromium | Cr % | 28.000 - 30.000 | | |
| Molybdenum | Mo % | 3.500 - 4.200 | | |
| Nickel | Ni % | 2.000 - 2.500 | | |
| C+N | C % + N % | 0.025 max. | Mechanical Properties | |
| Nitrogen | N % | 0.020 max. | Tensile Strength in Mpa | 485 min. |
| Copper | Cu % | 0.150 max. | Yield Strength in Mpa | 380 min. |
| Iron | Fe % | Balance | Elongation in % | 20 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in HB | 207 max. |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------------|--|
| Material | Standard | Country | untry Grade Belong to the Industry | |
| S44800 | UNS | USA | Plate, Sheet and Strip | |
| A268 29-4-2 | ASTM | USA | Plate, Sheet and Strip | |
| A497 S44800 | ASTM | USA | Plate, Bar and Forging | |
| SA-731 29-4-2 | ASME | USA | Casting | |
| A791 Grade 29-4-2 | ASTM | USA | Plate, Sheet and Strip | |
| SA-240 Type 29-4-2 | ASME | USA | Plate, Sheet and Strip | |
| A731 29-4-2 | ASTM | USA | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS