



Material - ASTM A608 Grade HW 50

Standard Specification for Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A608 Grade HW 50 Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 - 0.600		
Silicon	Si %	0.500 - 2.000		
Manganese	Mn %	1.500 max.	As - Cast	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	10.000 - 14.000		
Molybdenum	Mo %	0.050 max.		
Nickel	Ni %	58.000 - 62.000		-
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
N08001	UNS	USA	Casting	
G X 55 NiCr 60-12	UNI	Italy	Casting	
N08006	UNS	USA	Casting	
A297 Grade HW	ASTM	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.