

## Material - ASTM A608 Grade HX 50

Standard Specification for Castings, Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A 608/A 608M Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 - 0.600		
Silicon	Si %	0.500 - 2.000		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.	As - Cast	
Sulphur	S %	0.040 max.		
Chromium	Cr %	15.000 - 19.000		
Molybdenum	Mo %	0.050 max.		
Nickel	Ni %	64.000 - 68.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
N06006	UNS	USA	Casting	
G X 55 NiCr 60-12	UNI	Italy	Casting	
N06050	UNS	USA	Casting	
A297 Grade HX	ASTM	USA	Casting	
IS 4522 Grade 14	IS	India	Casting	
13505 Grade HX	IS	India	Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.