



## Material - ASTM A731 TP XM-8

Standard Specification for Castings, Seamless and Welded Ferritic Stainless Steel Pipe

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A731 TP XM-8 Seamless and Ferritic Stainless Steel Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	0.500 max.		
Ni+Cu	Ni% + Cu%	0.500 max.		
Nitrogen	N %	0.040 max.		
Aluminium	Al %	0.150 max.		
Titanium	Ti %	1.100 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-731 TP XM-8	ASME	USA	Pipes
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.