

Material - ASTM A732 5N

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.		
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.700 - 1.000	Annealing or Normalising or Hardening + Tempering	
Phosphorus	Р%	0.040 max.		lardening + Tempering
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.350 max.		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Other	Ot %	1.000 max.	Mechanical Properties	
Vanadium	V %	0.050 - 0.150	Tensile Strength in Mpa	586 min.
Mo + W	Mo% + W%	0.250 max.	Yield Strength in Mpa	379 min.
Iron	Fe %	Balance	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardne <mark>ss in BHN</mark>	-
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
6120	AISI	USA	Forging, Bar, Wire, and Shape	
J13052	UNS	USA	Casting	
200-400 W	JIS	Japan	Casting	
B2	BS	British	Forging	
B4	BS	British	Forging	
В5	BS	British	Casting	
B6	BS	British	Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS