

Material - ASTM A743 CN3M

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.030 max.	Solution Annealing	
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.000 - 22.000		
Nickel	Ni %	23.000 - 27.000		
Molybdenum	Mo %	4.500 - 5.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	435 min
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A351 CN3M	UNS	USA	Casting		
1.4585	DIN	Germany	Casting		
J94651	UNS	USA	Casting		
Ao X 10 CrNiMoCuNb 18-18	MSZ	Hungary	Casting		
G X 7 CrNiMoCuNb 18-18	DIN	Germany	Casting		
A351 CN3MN	ASTM	USA	Casting		
1.4588	ISO	International	Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.