

Material - ASTM A757 Grade A1Q

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing and Other Applications, for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A757 / A757M Steel Castings, Ferritic and Martensitic, for Pressure-Containing and Other Applications, for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.		
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.025 max.	Normalising or Annealing or	Hardening + Tempering
Sulphur	S %	0.025 max.		
Chromium	Cr %	0.400 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.250 max.		
Vanadium	V %	0.030 max.	Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	450 min.
Other	Ot %	1.000 max.	Yield Strength in Mpa	240 min.
Iron	Fe %	Balance	Elongation in %	24 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	17 min. @ -46°C

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A 216 WCB	ASTM	USA	Casting		
SA 216 WCB	ASME	USA	Casting		
J03002	UNS	USA	Casting		
1.0619	DIN	Germany	Casting		
1.0619	EN	European Union	Casting		
A660 WCB	ASTM	USA	Centrifugal Casting		
SA 660 WCB	ASME	USA	Centrifugal Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.