

Material - ASTM A990 CW-2M

Standard Specification for Castings, Iron-Nickel-Chromium and Nickel Alloys, Specially Controlled for Pressure Retaining Parts for Corrosive Service

Group - Non Ferrous Nickel Alloys

Sub Group - ASTM A990 CW-2M Iron-Nickel-Chromium and Nickel Alloys, Specially Controlled for Pressure Retaining Parts for Corrosive Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------------|----------|
| Carbon | C % | 0.020 max. | Solution Annealing | |
| Silicon | Si % | 0.800 max. | | |
| Manganese | Mn % | 1.000 max. | | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.015 max. | | |
| Chromium | Cr % | 15.000 - 17.500 | | |
| Iron | Fe % | 2.000 max. | | |
| Molybdenum | Mo % | 15.000 - 17.500 | | - |
| Tungsten | W % | 1.000 Max. | Mechanical Properties | |
| Nickel | Ni % | Balance | Tensile Strength in Mpa | 495 min. |
| - | - | - | Yield Strength in Mpa | 275 min. |
| - | - | - | Elongation in % | 20 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| - | - | - | - | | |
| - | - | ŀ | - | | |
| - | - | | - | | |
| - | - | - | - | | |
| - | - | - | - | | |
| - | - | - | - | | |
| - | - | - | - | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.