



Material - BDS 1.6220

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BDS 1.6220 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230		
Silicon	Si %	0.600 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 - 1.600		olizing or Hardoning and
Phosphorus	P %	0.020 max.		ŭ
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.150 max.		
Nickel	Ni %	0.800 max.		_
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.050 max.	Tensile Strength in Mpa	480 - 650
Iron	Fe %	Balance	Yield Strength in Mpa	300 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	50 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
AM2	BS	British	Casting	
2074/C3	AS	Australia	Casting	
1.622	ONORM	Australia	Casting	
1.622	EN	European Union	Casting	
1.622	DIN	Germany	Casting	
1.622	SS	Sweden	Casting	
1.622	UNE	Spain	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.