



Material - BS 10213 EN GX 5 CrNiMoNb 19-11-2

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 10213 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	9.000 - 12.000		
Molybdenum	Mo %	2.000 - 2.500		
Copper	Cu %	0.500 max.		
Niobium	Nb %	8×C - 1.000 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 440 - 640 Yield Strength in Mpa 210 min. Elongation in % 25 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 40 min. @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4581	EN	European Union	Casting
1.4581	BS	British	Casting
1.4581	DIN	Germany	Casting
GX5CrNiMoNb19-11-2	DIN	Germany	Casting
GX5CrNiMoNb19-11-2	AFNOR NF	France	Casting
GX5CrNiMoNb19-11-2	UNI	Italy	Casting
G X 6 CrNiMoNb 20 11	UNI	Italy	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.