



Material - BS 10216-2 EN 1.4903

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 10216-2 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.120	Normalising + Tempering	
Silicon	Si %	0.200 - 0.500		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	8.000 - 9.500		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.850 - 1.050		
Aluminium	Al %	0.040 max.		
Copper	Cu %	0.300 max.		
Niobium	Nb %	0.060 - 0.100	Mechanical Properties	
Vanadium	V %	0.180 - 0.250	Tensile Strength in Mpa	630 - 830
Nitrogen	N %	0.030 - 0.070	Yield Strength in Mpa	450 min.
Iron	Fe %	Balance	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	27 min. @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4903	EN	European Union	Steel
1.4903	DIN	Germany	Steel
X10CrMoVNb9-1	DIN	Germany	Steel
91	BS	British	Steel and Tube
J80490	UNS	USA	Casting
X10CrMoVNb9-1	ISO	International	Steel and Tube
TU Z 10 CDVNb 09 01	AFNOR NF	France	Steel and Tube

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.