



## Material - BS 10216-5 EN 1.4401

### Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 10216-5 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	16.500 - 18.500		
Nickel	Ni %	10.000 - 13.000		
Molybdenum	Mo %	2.000 - 2.500		
Nitrogen	N %	0.110 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      510 - 710 Yield Strength in Mpa      205 min. Elongation in %      30 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      60 min. @ -196°C	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
316L	AISI	USA	Bar, Wire, Strip, Slit, Plate, Sheet and Forging
1.4404	DIN	Germany	Cold Rolled, Strips, Slit Coils and Sheets
1.4404	EN	European Union	Rod, Bars, Wire and Forging
316 S 11	BS	British	Bright Bars, Hot Rolled and Cold Rolled Coil
SUS 316L	JIS	Japan	Hot Rolled Equal Leg Angles
03CH17N14M3	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging
ASTM A 351 CF3M	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.