



Material - BS 10216-5 EN 1.4959

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 10216-5 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.100	Solution Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.000 - 22.000		
Nickel	Ni %	30.000 - 34.000		
Copper	Cu %	0.500 max.		
Titanium	Ti %	0.250 - 0.650		
Aluminium	Al %	0.200 - 0.650		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 500 - 750 Yield Strength in Mpa 170 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 80 min. @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4959	EN	European Union	Steel
1.4959	DIN	Germany	Steel
X8NiCrAlTi32-21	DIN	Germany	Steel and Flat
1.4958	BS	British	Steel
1.4958	DIN	Germany	Steel
1.4958	EN	European Union	Steel
X5NiCrAlTi31 20	DIN	Germany	Steel and Flat

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.