



Material - BS 10216-5 EN X2CrNiMo18-14-3

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 10216-5 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	12.500 - 15.000		
Molybdenum	Mo %	2.500 - 3.000		
Nitrogen	N %	0.110 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 490 - 690 Yield Strength in Mpa 190 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 60 min. @ -196°C	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4436	BS	British	Steel
1.4436	DIN	Germany	Steel
X3CrNiMo17 13 3	UNI	Italy	Steel, Sheet, Plate and Strip
X3CrNiMo17 13 3	AFNOR NF	France	Steel
X3CrNiMo17 13 3	DIN	Germany	Sheet, Plate and Strip
316	SAE	USA	Steel, Wire, Bar, Shape and Forging
X2CrNiMo17 12 3	EN	European Union	Steel, Rod, Bar and Extrusion

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.