



Material - BS 310 C 40

Standard Specification for Austenitic Stainless Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 310 C 40 Austenitic Stainless Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.500	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	24.000 - 27.000		
Nickel	Ni %	19.000 - 22.000		
Molybdenum	Mo %	1.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 HK30	ASTM	USA	Casting
SA 351 HK30	ASME	USA	Casting
A608 HK30	ASTM	USA	Casting
F.8452	UNE	Spain	Casting
G X 40 CrNi 26-20	UNI	Italy	Casting
422952	CSN	Czech Republic	Casting
393 G-X 40 CrNi 25 20	SFS	Finland	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.