



Material - BS 3100 Grade 420C29

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 3100 Grade 420C29 Steel Castings for General Engineering Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.		
Silicon	Si %	1.000 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 max.		olizing or Hardoning and
Phosphorus	P %	0.040 max.		· ·
Sulphur	S %	0.040 max.		
Chromium	Cr %	11.500 - 13.500		
Nickel	Ni %	1.000 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	465 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	•
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
420C28	BS	British	Casting	
420	SAE	USA	Sheet, Strip and Plate	
420	AISI	USA	Forging	
A 176 S42000	ASTM	USA	Steel Plate, Sheet and Strip	
A 176 Type 420	ASTM	USA	Steel Plate, Sheet and Strip	
A 314 420	ASTM	USA	Billets and Bars for Forging	
A 314 S42000	ASTM	USA	Billets and Bars for Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.