



Material - BS 3100 Grade A2

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS 3100 Grade A2 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment			
Carbon	C %	0.350 max.	As Cast or Annealing or Normalizing or Hardening and Tempering			
Silicon	Si %	0.600 max.				
Manganese	Mn %	1.000 max.				
Phosphorus	P %	0.050 max.				
Sulphur	S %	0.050 max.				
Iron	Fe %	Balance				
-	-	-				
-	-	-	Mechanical Properties			
-	-	-			Tensile Strength in Mpa	490 min.
-	-	-			Yield Strength in Mpa	260 min.
-	-	-			Elongation in %	18 min.
-	-	-			Reduction of Area in %	-
-	-	-			Hardness in BHN	-
-	-	-			Impact in Joule	20 J @ RT
-	-	-				

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 216 WCB	ASTM	USA	Casting
SA 216 WCB	ASTM	USA	Casting
A660 Grade WCB	ASTM	USA	Casting
A660 Grade WCA	ASTM	USA	Casting
SA 216 WCA	ASME	USA	Casting
J02502	UNS	USA	Casting
1.0619	EN	European Union	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.