

Material - BS 434 S 20

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - BS 434 S 20 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Annealing or Hardening + Tempering	
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Molybdenum	Mo %	0.750 - 1.250		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	650 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S43400	ASTM	USA	Steel, Plate, Sheet and Strip		
S43400	UNS	USA	Steel		
51434	SAE	USA	Steel		
A651 TP 434	ASTM	USA	Steel and Tube		
A959 Type 434	ASTM	USA	Steel		
STS 434	KS	Korea	Steel, Wire and Rod		
SUS 434	JIS	Japan	Steel, Wire and Rod		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.