



Material - BS 503 LT 60

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS 503 LT 60 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.		
Silicon	Si %	0.600 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.800 max.		alizing or Hardoning and
Phosphorus	P %	0.030 max.		•
Sulphur	S %	0.030 max.		rig
Nickel	Ni %	3.000 - 4.000		
Iron	Fe %	Balance		
-	-	-		_
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	460 min.
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	134 - 187
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
BL2	BS	British	Casting	
2074/L3A	AS	Australia	Casting	
20 N12-M	AFNOR NF	France	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.