



Material - BS CrNi 18/9-0.03C/N

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS CrNi 18/9-0.03C/N Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Flat

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	8.500 - 11.500		
Nitrogen	N %	0.120 - 0.220		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 550- 750 Yield Strength in Mpa 270 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 55 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4311	EN	European Union	Tube
1.4311	DIN	Germany	Steel
1.4311	DIN	Germany	Steel
X3CrNi18-10	AFNOR NF	France	Steel and Tube
SUS 304 LN	JIS	Japan	Steel, Plate, Sheet and Strip
X20CrNiN 18-10	UNI	Italy	Sheet, Plate, Strip and Bar
X2CrNi18 10 KKW	ONORM	Australia	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.