GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10028-5 P355ML2 I 1.8833

Standard Specification for Flat Products Made of Steels for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10028-5 P355ML2 I 1.8833 Flat Products Made of Steels for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.140 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	1.600 max.
Phosphorus	P %	0.020 max.
Sulphur	S %	0.005 max.
Aluminium	Al %	0.020 min.
Nitrogen	N %	0.015 max.
Molybdenum	Mo %	0.200 max.
Niobium	Nb %	0.050 max.
Nickel	Ni %	0.500 max.
Titanium	Ti %	0.050 max.
Vanadium	V %	0.100 max.
Nb + Ti + V	Nb% + Ti% + V%	0.150 max.
Cr + Cu + Mo	Cr% + Cu% + Mo%	0.600 max.
Iron	Fe %	Balance

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	450 - 610
Yield Strength in Mpa	355 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	80 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10028-5 P355ML2 / FTStE 355 TM	DIN	Germany	Steel
SEW 084 FTStE 355 TM	DIN	Germany	Steel
EN 10028-5 1.8833	DIN	Germany	Steel
SEW 084 1.8833	DIN	Germany	Steel
10028-5 P355M	EN	European Union	Steel
10028-5 1.8821	EN	European Union	Steel
10028-5 1.8832	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.