GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10028-5 P420M I 1.8824

Standard Specification for Flat Products Made of Steels for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10028-5 P420M I 1.8824 Flat Products Made of Steels for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.160 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	1.700 max.
Phosphorus	P %	0.025 max.
Sulphur	S %	0.010 max.
Aluminium	Al %	0.020 min.
Nitrogen	N %	0.020 max.
Molybdenum	Mo %	0.200 max.
Niobium	Nb %	0.050 max.
Nickel	Ni %	0.500 max.
Titanium	Ti %	0.050 max.
Vanadium	V %	0.100 max.
Nb + Ti + V	Nb% + Ti% + V%	0.150 max.
Cr + Cu + Mo	Cr% + Cu% + Mo%	0.600 max.
Iron	Fe %	Balance

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	500 - 660
Yield Strength in Mpa	420 min.
Elongation in %	19 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	60 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10028-5 P 420 M	AFNOR NF	France	Steel
EN 10028-5 P 420 M	UNI	Italy	Casting
EN 10028-5 P420M / FStE 420 TM	DIN	Germany	Steel
EN 10028-5 1.8824	DIN	Germany	Steel
SEW 084 FStE 420 TM	DIN	Germany	Steel
SEW 084 1.8824	DIN	Germany	Steel
10028-5 1.8835	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.